

FLINTLASTIC® CAP 30 **MINERAL SURFACED, SBS MODIFIED BITUMEN** **FIBER GLASS CAP SHEET**

Product Information



Product Use: FLINTLASTIC Cap 30 Sheet is a glass mat cap sheet used in two-ply or multi-layer modified bitumen fire rated roofing systems. It is designed for use as a cap sheet over inorganic and organic built-up roofing systems. It may also be used as a heavy-duty, venting type base sheet when installed mineral side down and either mechanically fastened or spot mopped over lightweight insulating concrete decks or existing smooth surfaced membranes. FLINTLASTIC Cap 30 Sheet is suitable for both new construction and reroofing membranes over a variety of substrates. It is surfaced with ceramic granules to provide a durable, heat reflective weathering surface when used as a cap sheet. FLINTLASTIC Cap 30 Sheet is reinforced with a tough fibrous glass fabric.

Limitations: FLINTLASTIC Cap 30 Sheet is intended for hot asphalt application or approved cold adhesive such as CertainTeed's FlintBond™. Rolls should be stored upright, off ground, completely protected from the weather. Roof decks shall be structurally sound, dry, smooth and meet or exceed minimum requirements of the deck manufacturer, local code and CertainTeed. Additional specifications and precautions are contained in the CertainTeed Commercial Roof Systems Manual.

Product Composition and Features: FLINTLASTIC Cap 30 Sheet is reinforced with a durable, high quality fiber glass mat which receives a heavy coating of weathering grade, rubberized asphalt. FLINTLASTIC Cap 30 Sheet is manufactured on state of the art, dedicated roofing lines that were exclusively designed for the production of modified bitumen roofing membrane.

Roll Size: 39¾" X 32' 10"
Coverage*: One square

(*When applied according to CertainTeed's specification)

Approximate Weight: 87 lbs. per roll
Top Surface: Ceramic Granules
Back Surface: Mineral Release Agent

Applicable Standards: Meets ASTM D6163, Grade G, Type I.
Consult www.certainteed.com/lowslopetechinfo for details.

Technical Data

Modified Bitumen Coating: Non-oxidized (flux) asphalt, blended with a compatible elastomeric styrene-butadiene-styrene polymer and selected inert fillers.

Test Description	Test Method	Results*
Softening Point:	ASTM D36	260°F
Tensile Strength:	ASTM D5147	
	@ 73.4 +/- 3.6°F MD/XD	80/66 lbs./in.
	@ 0 +/- 3.6°F MD/XD	110/90 lbs./in.
Elongation:	ASTM D5147	
	@ 73.4 +/- 3.6°F MD/XD	4%/4%
	@ 0 +/- 3.6°F MD/XD	4%/4%
Dimensional Stability:	ASTM D5147 MD/XD	0.1/0.1 Max
Low Temperature Flex:	ASTM D5147	Pass @ -15°F
Compound Stability:	ASTM D5147	250°F
Thickness:	ASTM D5147	3.5mm (140 mils)
Tear Strength:	ASTM D5147	
	@ 73.4 +/- 3.6°F MD/XD	100/80 lbs.

***NOTE:** Published results are nominal production values confirmed by independent laboratory testing.

Product Application

FLINTLASTIC Cap 30 Sheet roof systems must be applied in accordance with installation procedures contained in the CertainTeed Commercial Roof Systems Manual. The following information is intended for general information purposes only and is not all-inclusive.

Preparation: Substrates to receive a roof system shall be firmly attached, smooth, dry, clean and free of depressions and sharp projections. Substrates requiring priming shall be primed with asphalt primer such as FlintPrime™ and be allowed to completely dry. Substrates shall provide positive drainage. Roof insulation shall be tapered to drains.

Installation: Unless otherwise specified by CertainTeed, a CertainTeed approved base sheet shall be installed with 3" sidelaps and 4" endlaps, with endlaps diagonally staggered not less than 3 feet apart. The base sheet shall be mechanically fastened to nailable substrates, and either solid or spot mopped in hot asphalt or cold applied to non-nailable or insulated substrates as specified in the CertainTeed Commercial Roof Systems Manual. Spot mopping, when specified, shall be applied in 9" diameter circles, 24" o.c. in all directions. Solid moppings shall be applied at the rate of 25 lbs. per 100 square feet. Over the base ply, solid mop one ply of FLINTLASTIC Cap 30 Sheet lapping 3" on sides and 6" on ends with endlaps diagonally staggered not less than 3 feet apart. Sides and endlaps shall be fully adhered in a complete mopping of hot asphalt with asphalt extending approximately 3/8" beyond lap edge. Refer to the CertainTeed Commercial Roof Systems Manual for additional specifications.

Precautions: Cold weather applications require special handling to prevent damage to the rolls and to ensure satisfactory installation. Do not apply roofing systems over improperly prepared substrates or substrates which contain moisture. Asphalt temperature at point of application shall not fall below 425°F to ensure maximum adhesion. Follow adhesive manufacturer's requirements when using cold adhesive.

Maintenance: CertainTeed Commercial Roof Systems do not require any additional maintenance beyond normal roof maintenance procedures. CertainTeed recommends regular roof maintenance and inspection to determine the condition of drains, flashings and other similar items, and to prolong the life expectancy of the roof system.

Warranties

CertainTeed offers a number of different types of Roof Membrane Warranties designed to meet the building owner's specific requirements. Please contact your nearest CertainTeed office for additional information and requirements.

Technical Assistance and Services

CertainTeed provides technical assistance in the design, selection, specification and application guidelines of FLINTLASTIC Roof Systems. Architectural and field representatives are available for consultation within each region.

For more information, contact CertainTeed's Customer Support at 800-233-8990.

ASK ABOUT ALL OF OUR OTHER CERTAINTEED® PRODUCTS AND SYSTEMS:

ROOFING • SIDING • TRIM • WINDOWS • DECKING • RAILING • FENCE
INSULATION • GYPSUM • CEILINGS • FOUNDATIONS • PIPE

www.certainteed.com <http://blog.certainteed.com>

CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482

Professional: 800-233-8990
Consumer: 800-782-8777

Rev 7/10 ©2010 CertainTeed Corporation, Printed in U.S.A.
Code No. COMM-266

