




## Product Information



# FLINTLASTIC® GTA™ COOLSTAR™

## APP MODIFIED BITUMEN ROLL ROOFING WITH HIGHLY REFLECTIVE COOLSTAR GRANULES



**Product Use:** FLINTLASTIC GTA COOLSTAR is designed for use as a roofing membrane over various types of substrates for both new construction and reroofing installations. It is suitable for most low sloped roof decks and may be used for roof system flashings including wall treatments, base flashings and field flashings.

**Limitations:** FLINTLASTIC GTA COOLSTAR is intended for torch application only and should not be exposed to adhesives or solvent based materials. Rolls should be stored upright, off ground, completely protected from the weather. Roof decks shall be structurally sound, dry, smooth and meet or exceed minimum requirements of the deck manufacturer, local code and CertainTeed. Additional specifications and precautions are contained in the CertainTeed Commercial Roof Systems Manual.

**Product Composition and Features:** FLINTLASTIC modified bitumen membranes are manufactured on state-of-the-art, dedicated roofing lines that were exclusively designed for the production of modified bitumen products. FLINTLASTIC GTA COOLSTAR is produced with a high performance, non-woven polyester mat which is impregnated and coated with a superior grade, modified bitumen compound, and surfaced with highly reflective CoolStar granules.

**Size:** 39<sup>3</sup>/<sub>8</sub>" X 32'10"

**Coverage\*:** One square

(\*When applied according to CertainTeed's specification)

**Approximate Weight:** 106 lbs. per roll

**Top Surface:** Highly reflective CoolStar granules

**Back Surface:** Torchable polyethylene film

**Applicable Standards:** FLINTLASTIC GTA COOLSTAR is approved by Underwriters Laboratories for use in various Class A, B, and C roof assemblies, with aggregate and other types of optional surfacings, by ICC-ES (ESR-1388), Factory Mutual, Miami-Dade, Florida Building Code Statewide Approval (FL479), Texas Department of Insurance and Cool Roof Rating Council. FLINTLASTIC GTA COOLSTAR is an approved ENERGY STAR® product. Initial Solar Reflectance: 0.74; Aged Solar Reflectance: 0.63; Initial Thermal Emittance: 0.88. Meets ASTM D6222, Grade G, Type I. Consult [www.certainteed.com/lowslopetechinfo](http://www.certainteed.com/lowslopetechinfo) for details.



## Technical Data

**Modified Bitumen Coating:** Non-oxidized (flux) asphalt, blended with various thermoplastic atactic polypropylene polymers and co-polymers.

**Support Mat:** High performance, puncture and tear resistant, non-woven polyester mat.

<u>Test Description</u>	<u>Test Method</u>	<u>Results*</u>
Solar Reflectance Index (SRI):	ASTM E1980	92.0
Softening Point:	ASTM D36	310°F
Tensile Strength:	ASTM D5147 @ 73.4 +/- 3.6°F MD/XD @ 0 +/- 3.6°F MD/XD	106/92 lbs./in. 133/116 lbs./in.
Elongation:	ASTM D5147 @ 73.4 +/- 3.6°F MD/XD @ 0 +/- 3.6°F MD/XD	57%/62% 20%/22%
Dimensional Stability:	ASTM D5147 MD/XD	0.5%/0.3%
Low Temperature Flex:	ASTM D5147	Pass @ 8°F
Compound Stability:	ASTM D5147	250°F
Thickness:	ASTM D5147	4.0mm (156 mils)
Tear Strength:	ASTM D5147 @ 73.4 +/- 3.6°F MD/XD	120/95 lbs.

\*NOTE: Published results are nominal production values confirmed by independent laboratory testing.

## **Product Application**

FLINTLASTIC modified bitumen roofing systems shall be applied in accordance with installation procedures contained in the CertainTeed Commercial Roof Systems Manual. The following information is intended for general information purposes only and is not all-inclusive.

**Preparation:** Substrates to receive a roof system shall be firmly attached, smooth, dry, clean and free of sharp projections and depressions. Substrates requiring priming shall be primed with asphalt primer such as CertainTeed's FlintPrime™ and be allowed to completely dry. Substrates shall provide positive drainage. Roof shall be tapered to drains.

**Installation:** Unless otherwise specified by CertainTeed, install one ply of GLASBASE® or other CertainTeed approved alternate base sheet lapping 2" on sides and 4" on ends. Base sheet shall be mechanically fastened to nailable substrates, and either solid or spot mopped in hot asphalt to non-nailable or insulated substrates as specified in the CertainTeed Commercial Roof Systems Manual. Apply base sheet in such a manner to provide and maintain a minimum 6" offset between side and end laps of base ply and FLINTLASTIC interply layers or finishing membrane. If specified, apply Flintlastic STA or STA Plus as an interply layer. Finally, install one ply of FLINTLASTIC GTA COOLSTAR lapping 3" on sides and 6" on ends with end laps diagonally staggered not less than 3 feet apart. Side and end laps should be inspected to ensure a minimum ⅜" flow of modified compound has been achieved. Asphalt bleed-out may be touched up with CoolStar granules.

**Precautions:** Cold weather applications require special handling to prevent damage to the rolls and to ensure satisfactory installation. Do not apply roofing systems over improperly prepared substrates or substrates which contain moisture. Follow all safety recommendations relating to the use and maintenance of liquid propane gas torches and equipment. Refer to the CertainTeed Commercial Roof Systems Specification Manual for additional safety information.

**Maintenance:** FLINTLASTIC Roof Systems do not require any additional maintenance beyond normal yearly roof maintenance procedures. CertainTeed recommends regular roof maintenance and inspection to determine the condition of drains, flashings and other similar items, and to prolong the life expectancy of the roof system.

## **Caution: Fire Hazard**

Torch application of this product may create a risk of FIRE, including SMOLDERING FIRES. The roofing applicator is solely responsible for ensuring and enforcing safe and proper application of CertainTeed's roofing products by competent and qualified personnel. Only properly trained roofing professionals are authorized to install this product.

Never apply flame directly to combustible materials or allow the flame to enter into hidden or protected areas that may contain combustible materials. Follow all local code requirements. Have a Class A-B-C fire extinguisher available to each applicator. Thoroughly inspect the job site whenever torching equipment has been used. Be certain that all chances of a fire have been eliminated.

Refer to the CertainTeed Commercial Roof Systems Manual, Midwestern Roofing Contractors Association (MRCA) CERTA program, National LP Gas Association, National Roofing Contractors Association (NRCA), National Fire Protection Association (NFPA), and Asphalt Roofing Manufacturers Association (ARMA) for further information and safety recommendations.

## **Warranties**

CertainTeed offers a number of different types of Roof Membrane Warranties designed to meet the building owner's specific requirements. Please contact your nearest CertainTeed office for additional information and requirements.

## **Technical Assistance and Services**

CertainTeed provides technical assistance in the design, selection, specification and application guidelines for all CertainTeed Roof Systems. Architectural and field representatives are available for consultation within each region.

For more information, contact CertainTeed's Customer Support at 800-233-8990.

### **ASK ABOUT ALL OF OUR OTHER CERTAINTEED® PRODUCTS AND SYSTEMS:**

ROOFING • SIDING • TRIM • WINDOWS • DECKING • RAILING • FENCE  
INSULATION • GYPSUM • CEILINGS • FOUNDATIONS • PIPE

[www.certainteed.com](http://www.certainteed.com) <http://blog.certainteed.com>

CertainTeed Corporation  
P.O. Box 860  
Valley Forge, PA 19482

Professional: 800-233-8990  
Consumer: 800-782-8777

Rev 3/11 ©2006 CertainTeed Corporation, Printed in U.S.A.  
Code No. COMM-193

